




**Part Number:** **SH-132026-2**

Revision 20190403 - Generated 2019-Apr-04



(If coated, Max./Min. includes coating)

|                            |  |                        |                      |
|----------------------------|--|------------------------|----------------------|
| <b>OD</b>                  | (nom. - bare core)<br>(max.)   | 33.02 mm<br>33.83 mm   | 1.300 in<br>1.332 in |
| <b>ID</b>                  | (nom. - bare core)<br>(min.)   | 19.94 mm<br>19.30 mm   | 0.785 in<br>0.760 in |
| <b>HT</b>                  | (nom. - bare core)<br>(max.)   | 11.18 mm<br>11.99 mm   | 0.440 in<br>0.472 in |
| <b>Mass</b>                | (approximate)  | 29 grams               |                      |
| <b>Magnetic Dimensions</b> | A <sub>e</sub> - Eff. Mag. Cross Section   | 0.698 cm <sup>2</sup>  |                      |
|                            | L <sub>e</sub> - Eff. Mag. Path Length   | 8.15 cm                |                      |
|                            | V <sub>e</sub> - Eff. Core Volume  | 5.69 cm <sup>3</sup>   |                      |
|                            | WA - Min. Eff. Window Area   | 2.93 cm <sup>2</sup>   |                      |
|                            | sa - Surface Area  | 40.6 cm <sup>2</sup>   |                      |
|                            | mlt - mean length per turn   | 4.82 cm                |                      |
| <b>Inductance</b>          | μ <sub>i</sub> (reference)   | 26                     |                      |
|                            | A <sub>L</sub> value (nominal)   | 28 nH/N <sup>2</sup>   |                      |
|                            | Test Winding   | N=70, #22 AWG          |                      |
|                            | Frequency  | 10 kHz                 |                      |
|                            | Voltage on Agilent 4284A   | 0.22 V                 |                      |
|                            | AL tolerance   | ±8%                    |                      |
| <b>Core Loss</b>           | $\text{Core Loss (mW/cm}^3\text{)} = \frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$ |                        |                      |
|                            | where B <sub>pk</sub> expressed in gauss, f expressed in hertz, and:<br>a=1.000E+06, b=3.287E+08, c=5.779E+06, d=1.240E-14                         |                        |                      |
|                            | B <sub>pk</sub>  | 500 G                  |                      |
|                            | frequency  | 100 kHz                |                      |
|                            | Core Loss (nominal)  | 277 mW/cm <sup>3</sup> |                      |
| Core Loss (maximum)        | 318 mW/cm <sup>3</sup>   |                        |                      |
| <b>DC Saturation</b>       | $\% \mu_i = \frac{1}{a + b \cdot H^c} + d$   |                        |                      |
|                            | where H expressed in oersteds, and:<br>a=1.000E-02, b=1.042E-06, c=1.701, d=0.000  |                        |                      |
|                            | H <sub>DC</sub>  | 200 Oe                 |                      |
|                            | Percent Initial Perm(nom.)   | 53.9%                  |                      |
| Percent Initial Perm(min.) | 46.1%  |                        |                      |
| <b>Coating/Pkg</b>         | Coating Type:  | Blue Epoxy             |                      |
|                            | Voltage Breakdown (min.)   | 1000 Vrms              |                      |
|                            | Limit  | 0.1 mA, 5 s            |                      |
|                            | Package Quantity   | 448 Pcs/Box            |                      |

|                      |                     |        |       |       |        |        |         |         |         |         |         |         |       |
|----------------------|---------------------|--------|-------|-------|--------|--------|---------|---------|---------|---------|---------|---------|-------|
| <b>Winding Table</b> | <b>Wire Size</b>    | AWG    | 8     | 10    | 12     | 14     | 16      | 18      | 20      | 22      | 24      | 26      | 28    |
|                      |                     | mm     | 3.150 | 2.500 | 2.000  | 1.600  | 1.250   | 1.000   | 0.800   | 0.630   | 0.500   | 0.400   | 0.315 |
|                      | <b>Single Layer</b> | Turns  | 14    | 18    | 22     | 29     | 36      | 46      | 58      | 73      | 91      | 114     | 142   |
|                      |                     | Rdc(Ω) | 1.4 m | 2.8 m | 5.5 m  | 11.6 m | 22.8 m  | 46.3 m  | 92.9 m  | 186.0 m | 368.8 m | 734.8 m | 1.5   |
| <b>Full Winding</b>  | Turns               | 15     | 24    | 37    | 57     | 88     | 136     | 211     | 326     | 504     | 780     | 1,208   |       |
|                      | Rdc(Ω)              | 1.5 m  | 3.8 m | 9.3 m | 22.7 m | 55.7 m | 137.0 m | 338.1 m | 830.8 m | 2.0     | 5.0     | 12.4    |       |

